





Features

- •Kyocera's series of Multilayer Ceramic Chip Capacitors are designed to meet a wide variety of needs. We offer a complete range of products for both general and specialized applications.
- •We have a network worldwide in order to supply our global customer bases quickly and efficiently.
- •All our products are highly reliable due to their monolithic structure of high-purity and superfine uniform ceramics and their integral internal electrodes.
- •Our stringent quality control in every phase of production from material procurement to shipping ensures consistent manufacturing and superior quality.
- Kyocera components are available in a wide choice of dimensions, temperature characteristics, rated voltages, and terminations to meet specific configurational requirements.

■KYOCERA PART NUMBER

OPTION:

Above digits are used to track individual specification or thickness.

(Example) 1) Series 2) Size : CM Series(General) : 0201

(2) Size . U2 U1
(3) Dielectric : X5R
(4) Capacitance : 2.2 μF
(5) Tolerance : ±20%
(6) Voltage : 6.3 Vdc
(7) Termination : Sn
(8) Packaging : Cavity pitch 2mm / Reel Size φ180

(1) SERIES CODE

CODE	Туре
CM	General
СТ	Low Profile
CU	High-Q
KNH	Three Terminal Capacitors

(2) SIZE CODE

CODE	EIA	JIS
02	01005	0402
03	0201	0603
05	0402	1005
105	0603	1608
21	0805	2012
316	1206	3216
32	1210	3225

3 DIELECTRIC CODE

T	Temperature Compensation Type						
CODE Temperature Range (°C) ppm/°C							
CG	FF 4- 10F	G -55 to 125 0	0	±30			
СН	-55 (0 125	U	±60				

- All parts of COG will be marked as "CG" but will conform to the above table.
- Temperature coefficients are determined by calculation based on measurement at 20°C and 85°C.

	High Dielectric Constant Type							
CODE	Temperature Range (°C)	∆C max. (%)	Standard Temperature (°C)					
X5R	-55 to 85	±15						
X6S	-55 to 105	±22						
X6T	-33 10 103	+22/-33	25					
X7R		±15	23					
X7S	-55 to 125	±22						
X7T		+22/-33						

4 CAPACITANCE CODE

Capacitance expressed in pF. Two significant digits plus number of zeros. For Values < 10pF, Letter R denotes decimal point, $<1,000pF=1nF,1,000nF=1\mu F>$ (Example)

CODE	Capacitance
R50	0.5pF
1R0	1pF
100	10pF
101	100pF
102	1nF
103	10nF
104	100nF
105	1µF
106	10µF
107	100µF

E STANDARD NUMBER							
E3	E6	E12	E24				
	1.0	1.0	1.0	1.1			
1.0	1.0	1.2	1.2	1.3			
1.0	1.5	1.5	1.5	1.6			
	1.5	1.8	1.8	2.0			
	2.2	2.2	2.2	2.4			
2.2	2.2	2.7	2.7	3.0			
2.2	3.3	3.3	3.3	3.6			
	3.5	3.9	3.9	4.3			
	4.7	4.7	4.7	5.1			
4.7	4.7	5.6	5.6	6.2			
4.7	6.8	6.8	6.8	7.5			
	0.0	8.2	8.2	9.1			

(5) TOLERANCE CODE

Temperature Compensation Type (C0G)					
CODE	Tolerance				
A*	±0.05pF				
В	±0.1pF				
С	±0.25pF ±0.5pF				
D					
G*	±2%				
J	±5%				
K	±10%				

^{*:} Option

High Dielectric Constant Type					
(X5R/X6S/X6T/X7R/X7S/X7T)					
CODE Tolerance					
J* ±5%					
K ±10%					
М	±20%				

^{*:} Option

(6) VOLTAGE CODE

CODE	Rated Voltage
02	2.5Vdc
04	4Vdc
06	6.3Vdc
10	10Vdc
16	16Vdc
25	25Vdc
35	35Vdc
50	50Vdc
100	100Vdc

7TERMINATION CODE

CODE	ODE Termination							
A Nickel Barrier/ Ti								
• Please is need	contact us if Au terminaled.	ation						

® PACKAGING CODE


CODE	Size Code	Cavity pitch	Reel size	
Т	105 to 32	4mm		
Н	02 to 05	5 2mm		
Q	03/05	1mm	φ180	
Р	02	1mm		
L	105 to 32	4mm		
N	02 to 05	2mm	φ330	
W	03/05	1mm		






Dimension

■CM/CT/CU Series




■Packaging Code



Size	Code		Dimension			Dimension (mm)			Quantity	per reel			
Size	EIA	JIS	Code	L	W	Т	P min.	P max.	P to P min.	φ180 Reel	φ330 Reel			
02	01005	0402	А	0.4±0.02	0.2±0.02	0.2±0.02	0.07	0.14	0.13	40kp(E4/1) 20kp(P8/2)	- 80kp(P8/2)			
			A B	0.6±0.03	0.3±0.03	0.22 max. 0.3±0.03	0.1	0.2	0.2	30kp(P8/1)	150kp(P8/1)			
03	0201	0603	С	0.6±0.05	0.3±0.05	0.3±0.05				15kp (P8/2)	50kp(P8/2)			
03	0201	0603	D E	0.6±0.09	0.3±0.09	0.22 max. 0.3±0.09	0.13	0.23	0.19	15kp (P8/2)	50kp(P8/2)			
			F	0.0±0.03	0.5±0.05	0.5±0.05				10kp(P8/2)	_			
			А			0.22 max.								
			В	1.0±0.05	0.5±0.05	0.33 max.				20kp(P8/1)	100kp(P8/1)			
			С			0.5±0.05				10kp (P8/2)	50kp (P8/2)			
			D	1.0±0.1	0.5±0.05	0.22 max.	0.15		0.3	10kp(P8/2)	50kp(P8/2)			
٥٢	0.400	1005	Е	1.0±0.15	0.5±0.15	0.5±0.15		0.35		10kp(P8/2)	40kp(P8/2)			
05	0402	1005	F			0.33 max.				10kp(P8/2)	. –			
			G			0.5 max.				10kp(P8/2)	50kp(P8/2)			
			Н	1.0±0.2	0.5±0.2	0.55 max.	1			10kp(P8/2)	50kp(P8/2)			
			J		[0.5±0.2	1							10kp(P8/2)
			K			0.8 max.	1			10kp(P8/2)	30kp(P8/2)			
		A 1.6±0.1 0.8±0.1 0.55 max.												
105	0603	1608	В	1.0±0.1	0.6±0.1	0.8±0.1	0.2	0.2 0.6 0.5	0.2 0.6 0.5 4kp(P8/4)	Alm (D0/A)	10kp(P8/4)			
105	0003	1000	С	1.6±0.15	0.8±0.15	0.8±0.15	0.2			0.0	0.0	0.5 4kp(P6/4)	тикр(10/4)	
			D	1.6±0.2	0.8±0.2	0.8±0.2								
			В	2.0±0.1	1.25±0.1	1.25±0.1				3kp (E8/4)	10kp (E8/4)			
21 08	0805	2012	С	2.0±0.15	1.25±0.15	0.95 max.	0.2	0.2 0.75	75 0.7	4kp (P8/4)	10kp(P8/4)			
	0003	305 2012	Е	2.0±0.2	1.25±0.2	0.95 max.				4kp (P8/4)	10kp(P8/4)			
			F	∠.∪±∪.∠		1.25±0.2				3kp (E8/4)	10kp(E8/4)			
			Α	3.2±0.2	1.6±0.15	1.6±0.15	0.3	0.85	1.4	2.5kp (E8/4)	5kp(E8/4)			
316	1206	3216	В		1.6±0.2	1.6±0.2					3kp(E0/4)			
			С	3.2±0.3	1.6±0.3	1.6±0.3	0.3	0.85	1.9	2kp (E8/4)	_			
32	1210	3225	Α	3.2±0.3	2.5±0.2	2.5±0.2	0.3	1.0	1.4	1kp (E8/4)	4kp(E8/4)			

■KNH Series



Size	Со	de	Dimension			Dimension	(mm)			Packa	aging
Size	EIA	JIS	Code	L	W	Т	G	Р	R	φ180 Reel	φ330 Reel
VNILI .	0402		Α	1.0±0.1	0.5±0.2	0.5 max.					
KNH 05		1005	В	1.0±0.15	0.5±0.15	0.5±0.15	0.3±0.1	0.15±0.1	≥0.05	10kp(P8/2)	_
05			С	1.0±0.2	0.5±0.2	0.5 ± 0.2					





RoHS Compliant Products


■Features

We offer a diverse product line ranging from ultra-compact (0.4×0.2mm) to large (3.2×2.5mm) components configured for a variety of temperature characteristics, rated voltages, and packages. We offer the choice and flexibility for almost any applications.

■Applications

This standard type is ideal for use in a wide range of applications, from commercial to industrial equipment.

Temperature Compensation Dielectric



(EIA	ize Code)		CN (010			CM03 (0201)	
	oltage(Vdc) acitance	1	16	25		50	
1R0 1R5	1 pF 1.5 pF				П		
2R0 3R0 4R0	2 pF 3 pF 4 pF						
5R0 6R0 7R0	5 pF 6 pF 7 pF			А			
8R0 9R0 100	8 pF 9 pF 10 pF 12 pF						
120 150 180	15 pF 18 pF					В	
220 270 330	22 pF 27 pF 33 pF						
390 470 560	39 pF 47 pF 56 pF		А				
680 820 101	68 pF 82 pF 100 pF						
121 151 181	120 pF 150 pF 180 pF						
221	220 pF		Α	· ·	Ţ		_

Standard Capacitor Value: E12 Series>

Please contact for capacitance value other than standard.

Please refer to here for the test method and specifications of Standard Specification 1.

Alphabets in capacitance chart denote dimensions. Please refer to the below table for detail.

(Example) In case of "B" for CM03;

L: 0.6±0.03mm, W: 0.3±0.03mm, T: 0.3±0.03mm

		D	imansian (mr	n)					Packa	aging				
Size	Dimension	D	imension (mr	n)			φ180 Reel					φ330 Reel		
3126	Code	L	W	Т	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	Code	Quantity	Taping Material	Taping Width	Cavity Pitch
02	A	0.4±0.02	0.2+0.02	0.2±0.02	Р	40,000	Plastic	4mm	1mm	_	_	_	_	_
02	A		0.2±0.02	0.2±0.02	Н	20,000	Paper	8mm	2mm	N	80,000	Paper	8mm	2mm
03	В	0.6+0.03	0.3+0.03	0.3±0.03	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm
03		0.6±0.03	0.3±0.03	U.5±U.U3	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm





RoHS Compliant Products

X5R Dielectric

 Capacitance chart Standard Spec.1 Standard Spec.2 Optional Spec.

Size (EIA Code)	(CM02 (01005))			CM03 (0201)					CM05 (0402) 6.3 10 16			
Rated Voltage (Vdc) Capacitance	6.3	10	16	4	6.3	10	16	25	4	6.3	10	16	25	35
101 100 pF 151 150 pF 221 220 pF 331 330 pF 471 470 pF														
151 150 pF 221 220 pF 331 330 pF 471 470 pF 102 1000 pF 152 1500 pF 222 2200 pF 332 3300 pF			A8											
681 680 pF 102 1000 pF 152 1500 pF 222 2200 pF 332 3300 pF 472 4700 pF 682 6800 pF 103 10000 pF 153 15000 pF 223 22000 pF								В3						
472 4700 pF 682 6800 pF 103 10000 pF 153 15000 pF 223 22000 pF 333 33000 pF	A8													
333 33000 pF 473 47000 pF 683 68000 pF 104 0.1 µF 224 0.22 µF		A8				В7	[7 E8 7]	[E8 2]				C8	C3	
474 0.47 μF 105 1 μF 225 2.2 μF 475 4.7 μF 106 10 μF 156 15 μF	A8				B8 C8 C8/E8	C8 E10	E10	V 10 //			C7	C7 C8	C7 H8/J8	C7
224 0.22 µF 474 0.47 µF 105 1 µF 225 2.2 µF 475 4.7 µF 106 10 µF 156 15 µF 226 22 µF 476 47 µF				E8	F9				E8 J8	J8 E8 ₹J8 ₹K8	ZE8 7 J8 7	J8	J8	

(8	Size CM105 (0603) ated Voltage(Vdc) 6.2 4.0 4.6 2.5 2.3								CN (08	121 805)				CM (12	316 06)		CM32 (1210)		
	ted Voltage(Vdc) Capacitance	6.3	10	16	25	35	4	6.3	10	16	25	50	16	25	50	100	16	25	50
105	5 1 μF				C8							B8							
225 475 106	5 2.2 μF 5 4.7 μF 5 10 μF		C8	B8	D8	D8 D9				F8	F8			A3 B8	В3	В3	A3	A8	A3
226 476 107	5 22 μF 5 47 μF	☑ D8 ☑	D8	D8			☑ F8 ②	F7	F8		F8		B8					Ao	

<Standard Capacitance Value>

Capacitance value of less than $0.1 \mu F$:E6 Series

Capacitance value of $0.1\mu F$ and larger :E3 Series

Please contact for capacitance value other than standard.
Please refer to here for the test method and specifications of Standard Specification 1.

Please refer to here for the test method and specifications of Standard Specification 2.

Two digits alphanumerics in capacitance chart denote dimensions and $\tan \delta$. Please refer to the above table for detail.

(Example) In case of "B3" for CM03; L: 0.6 ± 0.03 mm, W: 0.3 ± 0.03 mm, T: 0.3 ± 0.03 mm, Tan δ : 5.0% max.

lan δCode	Tan δ
3	5.0% max.
7	10.0% max.
8	12.5% max.
9	15.0% max.
10	20.0% max.

		D	imension (mr	m)					Packa	aging				
Size	Dimension	D	imension (iiii	11)			φ180 Reel					φ330 Reel		
Size	Code	L	W	Т	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	Code	Quantity	Taping Material	Taping Width	Cavity Pitch
02	Α	0.4±0.02	0.2±0.02	0.2±0.02	Р	40,000	Plastic	4mm	1mm	_	_	-	_	_
02	_ A	0.4±0.02	0.2±0.02	0.2±0.02	Н	20,000	Paper	8mm	2mm	N	80,000	Paper	8mm	2mm
	В	0.6±0.03	0.3±0.03	0.3±0.03	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm
	В	0.0±0.03	0.5±0.03	0.5±0.05	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
03	C	0.6±0.05	0.3±0.05	0.3±0.05	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm
03					Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
	Е	0.6±0.09	0.3±0.09	0.3±0.09	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
	F	0.6±0.09	0.3±0.09	0.5±0.05	Н	10,000	Paper	8mm	2mm	_	_	ı	_	_
	С	1.0±0.05	0.5±0.05	0.5±0.05	Q	20,000	Paper	8mm	1mm	W	100,000	Paper	8mm	1mm
		1.0±0.03	0.5±0.05	0.5±0.05	Н	10,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
05	Е	1.0±0.15	0.5±0.15	0.5±0.15	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm
03	Н	1.0±0.2	0.5±0.2	0.55 max.	Н	10,000	Paper	8mm	2mm	_	_	_	_	_
	J	1.0±0.2	0.5±0.2	0.5±0.2	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm
	K	1.0±0.2	0.5±0.2	0.8 max.	Н	10,000	Paper	8mm	2mm	N	30,000	Paper	8mm	2mm
	В	1.6±0.1	0.8±0.1	0.8±0.1	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm
105	С	1.6±0.15	0.8±0.15	0.8±0.15	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm
	D	1.6±0.2	0.8±0.2	0.8±0.2	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm
21	В	2.0±0.1	1.25±0.1	1.25±0.1	T	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm
21	F	2.0±0.2	1.25±0.2	1.25±0.2	T	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm
316	Α	3.2±0.2	1.6±0.15	1.6±0.15	T	2,500	Plastic	8mm	4mm	L	5,000	Plastic	8mm	4mm
310	В	3.2±0.2	1.6±0.2	1.6±0.2	T	2,500	Plastic	8mm	4mm	L	5,000	Plastic	8mm	4mm
32	А	3.2±0.3	2.5±0.2	2.5±0.2	T	1,000	Plastic	8mm	4mm	L	4,000	Plastic	8mm	4mm





RoHS Compliant Products

X6S/X6T Dielectric

Cap	acitance d	hart	Star	ndard Sp	ec.2 <table-cell></table-cell>	Option	al Spec.										
	Size A Code)		CN (02					105 .02)			CM (06	105 03)			CN (08		
	Voltage (Vdc) pacitance	2.5	4	6.3	10	4	6.3	10	16	4	6.3	10	16	4	6.3	10	16
103	10000 pF																
153 223 333	15000 pF 22000 pF 33000 pF																
473 683 104	47000 pF 68000 pF 0.1 μF																
224 474 105	0.22 μF 0.47 μF 1 μF		E10	E10	E10 3			C8	∑ C8 ∑								
225 475 106	2.2 μF 4.7 μF 10 μF	F9 3					E8/J8					D9	Ø D9 Ø				
226 476 107	22 μF 47 μF 100 μF					₹ K8 ∑				D8 // D8 //	D8	<u> </u>		F7 F8 2	F8	F8	F8

Į			X6T	
	Size (EIA Code)		CM03 (0201)	
	Rated Voltage (Vdc) Capacitance	2.5	4	10
	224 0.22 μF 474 0.47 μF 105 1 μF	C8 2 E8 2		E8 2
	225 2.2 μF 475 4.7 μF 106 10 μF	E8 2	E8 3	

< Standard Capacitor Value: E3 Series >
Please contact for capacitance value other than standard.
Please refer to here for the test method and specifications of Standard Specification 2.

Two digits alphanumerics in capacitance chart denote dimensions and $\tan \delta$. Please refer to the above table for detail. (Example) In case of "D9" for CM105; L: 1.6 ± 0.2 mm, W: 0.8 ± 0.2 mm, T: 0.8 ± 0.2 mm, Tan δ : 15.0% max.

lan δCode	Tan δ
7	10.0% max.
8	12.5% max.
9	15.0% max.
10	20.0% max.

			D	imension (mr	m)					Packa	aging				
	ize	Dimension	D		11)			φ180 Reel					φ330 Reel		
	oize	Code	L	W	Т	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	Code	Quantity	Taping Material	Taping Width	Cavity Pitch
		С	0.6±0.05	0.3±0.05	0.3±0.05	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm
	03		0.0±0.03	U.5±U.U5	0.5±0.05	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
	05	Е	0.6±0.09	0.3±0.09	0.3±0.09	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
		F	0.6±0.09	0.3±0.09	0.3±0.05	Н	10,000	Paper	8mm	2mm	_	_	-	-	_
		С	1.0±0.05	0.5±0.05	0.5±0.05	Q	20,000	Paper	8mm	1mm	W	100,000	Paper	8mm	1mm
		C	1.0±0.05	0.5±0.05	0.5±0.05	Н	10,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm
	05	E	1.0±0.15	0.5±0.15	0.5±0.15	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm
		J	1.0±0.2	0.5±0.2	0.5±0.2	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm
		K	1.0±0.2	0.5±0.2	0.8 max.	Н	10,000	Paper	8mm	2mm	N	30,000	Paper	8mm	2mm
-	105	D	1.6±0.2	0.8±0.2	0.8±0.2	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm
	21	F	2.0±0.2	1.25±0.2	1.25±0.2	Т	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm





RoHS Compliant Products

X7R Dielectric

•Capacitance o	hart	Stan	dard Sp	ec.1	Standa	rd Spec.2	2 💹 Op	otional S	рес.			
Size (EIA Code)	CM02 (01005)	CM03 (0201)	CN (04			CM (06	105 03)			CN (08		
Rated Voltage(Vdc) Capacitance	16	10	6.3	25	6.3	10	16	25	6.3	16	25	50
101 100 pF 151 150 pF 221 220 pF 331 330 pF 471 470 pF 681 680 pF 102 1000 pF 152 1500 pF 222 2200 pF 332 3300 pF 472 4700 pF 682 6800 pF 103 10000 pF 153 15000 pF	8A	В3										
223 22000 pF 333 33000 pF 473 47000 pF 683 68000 pF 104 0.1 µF				C8								
224 0.22 µF 474 0.47 µF 105 1 µF 225 2.2 µF 4.7 µF 106 10 µF			<u> </u>		C8	B8	B8	В3	F8	F8	B8 F8	F3

	Size (EIA Code)			CM316 (1206)			CM32 (1210)					
Rated Voltage (Vdc) Capacitance		6.3	10	16	25	50	16	25	50			
	225 2.2 μF 475 4.7 μF 106 10 μF			B8	В3	В3		A8	A3			
	226 22 µF	B8	B5				A8					

<Standard Capacitance Value>

Capacitance value of less than $0.1\mu F$: E6 Series $\,$ / Capacitance value of $0.1\mu F$ and larger : E3 Series

Please contact for capacitance value other than standard.
Please refer to here for the test method and specifications of Standard Specification 1.
Please refer to here for the test method and specifications of Standard Specification 2.

Two digits alphanumerics in capacitance chart denote dimensions and $\tan \delta$. Please refer to the above table for detail.

(Example) In case of "B3" for CM03; L: 0.6 ± 0.03 mm, W: 0.3 ± 0.03 mm, T: 0.3 ± 0.03 mm, Tan δ : 5.0% max.

Tan δCode	Tan δ
3	5.0% max.
5	7.5% max.
8	12.5% max.

		Dimension (mm)							Packa	aging							
Size	Dimension	D	Difficusion (min)			φ180 Reel					φ330 Reel						
3126	Code	L	W	Т	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	Code	Quantity	Taping Material	Taping Width	Cavity Pitch			
02	А	0.4±0.02	0.2±0.02	0.2±0.02	Р	40,000	Plastic	4mm	1mm	_	_	_	_	_			
02					Н	20,000	Paper	8mm	2mm	N	80,000	Paper	8mm	2mm			
03	В 0.6:	0.6±0.03	0.3±0.03	0.2.0.02	0.2 0.02	0.2 + 0.02	0.3±0.03	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm
03		0.0±0.05		0.5±0.03	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm			
٥٢	С	1.0±0.05	0.5±0.05	5 0.5±0.05	Q	20,000	Paper	8mm	1mm	W	100,000	Paper	8mm	1mm			
05					Н	10,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm			
105	В	1.6±0.1	0.8±0.1	0.8±0.1	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm			
105	С	1.6±0.15	0.8±0.15	0.8±0.15	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm			
21	В	2.0±0.1	1.25±0.1	1.25±0.1	T	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm			
21	F	2.0±0.2	1.25±0.2	1.25±0.2	T	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm			
316	В	3.2±0.2	1.6±0.2	1.6±0.2	T	2,500	Plastic	8mm	4mm	L	5,000	Plastic	8mm	4mm			
32	Α	3.2±0.3	2.5±0.2	2.5±0.2	T	1,000	Plastic	8mm	4mm	L	4,000	Plastic	8mm	4mm			





RoHS Compliant Products

X7S/X7T Dielectric

Standard Spec.1 Standard Spec.2 Optional Spec. •Capacitance chart

		X7S								X	7T		
Size (EIA Code)	CM03 (0201)			CM21 (0805)	CM (12	316 06)	CM03 (0201)	CM05 (0402)			CM21 (0805)		
Rated Voltage (Vdc) Capacitance	6.3	4	6.3	10	100	10	100	6.3	10	6.3	10	6.3	10
104 0.1 μF	B7 2												
224 0.22 μF 474 0.47 μF 105 1 μF		C8	C8		F3			€ E8 ②					
225 2.2 μF 475 4.7 μF 106 10 μF		E3	E3 🖔	E3 Ø			B3 C3		∑ 18 ∑	D9	D8		
226 22 µF						B5						F8	F8 🛭

Standard Capacitor Value: E3 Series>
Please contact for capacitance value other than standard.
Please refer to here for the test method and specifications of Standard Specification 1.
Please refer to here for the test method and specifications of Standard Specification 2.

Two digits alphanumerics in capacitance chart denote dimensions and $\tan \delta$. Please refer to the above table for detail.

(Example) In case of "D9" for CM105; L: 1.6±0.2mm, W: 0.8±0.2mm, T: 0.8±0.2mm, Tanδ: 15.0% max.

Tan δCode	Tan δ
3	5.0% max.
5	7.5% max.
7	10.0% max.
8	12.5% max.
9	15.0% max.

	Dimension Code	Dimension (mm)			Packaging										
Size		Di	Diffiction (IIIII)			φ180 Reel					φ330 Reel				
Size		Code L	W	Т	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	Code	Quantity	Taping Material	Taping Width	Cavity Pitch	
						20.000				144	150,000				
	В	0.6±0.03	0.3±0.03	0.3±0.03	Q	30,000	Paper	8mm	1mm	W	150,000	Paper	8mm	1mm	
03	В	0.0±0.03			Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm	
	Е	0.6±0.09	0.3±0.09	0.3±0.09	Н	15,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm	
	C 1.0±0.05	0.5±0.05	0.5±0.05	Q	20,000	Paper	8mm	1mm	W	100,000	Paper	8mm	1mm		
05		1.0±0.05	0.5±0.05	0.5±0.05	Н	10,000	Paper	8mm	2mm	N	50,000	Paper	8mm	2mm	
05	Е	1.0±0.15	0.5±0.15	0.5±0.15	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm	
	J	1.0±0.2	0.5±0.2	0.5±0.2	Н	10,000	Paper	8mm	2mm	N	40,000	Paper	8mm	2mm	
105	D	1.6±0.2	0.8±0.2	0.8±0.2	T	4,000	Paper	8mm	4mm	L	10,000	Paper	8mm	4mm	
21	F	2.0±0.2	1.25±0.2	1.25±0.2	T	3,000	Plastic	8mm	4mm	L	10,000	Plastic	8mm	4mm	
316	В	3.2±0.2	1.6±0.2	1.6±0.2	Т	2,500	Plastic	8mm	4mm	L	5,000	Plastic	8mm	4mm	
310	С	3.2±0.3	1.6±0.3	1.6±0.3	T	2,000	Plastic	8mm	4mm	_	_	_	_	_	





Test Conditions and Standards

Test Conditions and Specifications for Temperature Compensation Type (C Δ Characteristics) CM / CU Series (Standard Spec.1)

Test	Items		ī	est Conditions			Specifications		
Capacitance Va	lue (C)		Capacitance	Frequency	Volt		Within tolerance		
Q			C≤1000pF C>1000pF	45411 1400/).5 to 5Vrms		C≥30pF: Q≥1000 C<30pF: Q≥400+20C		
Insulation Resis	tance (IR)	and humidity	/.	ninute, and meas rent of the capaci	Over $10000M\Omega$ or $500M\Omega$ • μ F, whichever is less				
Dielectric Resist	tance	*CU02C△R20	-120/25V: twice	tage for 1 to 5 se		cceed 50mA.	No problem observed		
Appearance		Microscope					No problem observed		
Termination Str	ength		vard force of 500 0201 size, and 1N	g (5N) to a PCB-r I for 01005 size.	nounted sampl	e.	No problem observed		
Bending Streng	th	Glass epoxy P	CB: Fulcrum spac	cing: 90mm, dura	tion time 10 sec	conds.	No significant damage with 1mm bending.		
Vibration Test	Appearance	Vibration free	uency: 10 to 55	(Hz)	No problem observed				
	ΔC	Amplitude: 1.	5mm		V V 17 "	.: 0	Within Tolerance		
	Q		ndition: 10→55→ hours in total.	10Hz/ 1 minute ii	n X, Y and Z dir	ections: 2	C≥30pF: Q≥1000 C<30pF: Q≥400+20C		
Soldering	Appearance			solder for 10±0.	No problem observed				
Heat Resistant	ΔC	mal temperat (Pre-heating of		y, and measure th	Within±2.5% or±0.25pF, whichever is larger				
Resistant	Q	Order Temperature Time					C≥30pF: Q≥1000 C<30pF: Q≥400+20C		
	IR			150 to 200°C	2 minutes		Over $10000M\Omega$ or $500M\Omega$ • μ F whichever is less		
	Withstanding Voltage		nd discharge cur hstanding voltag	rent of the capaci ge measurement.	Resist without problem				
Solderablity		Soaking cond	Sn-3Ag-0.5Cu Sn63 Solder	245±5°C 235±5°C	3±0.5 sec. 2±0.5 sec.		Solder coverage : 95% min.		
Temperature	Appearance	(Cl-)					No problem observed		
Cycle	ΔC	(Cycle) Room temper	rature (3 min.)→				Within±2.5% or ±0.25pF, whichever is larger		
	Q	Room temper	tion temperature rature (3 min.)→ ation temperatur				C≥30pF: Q≥1000 C<30pF: Q≥400+20C		
	IR	After 5 cycles	, measure after 2	4±2 hours.			Over $10000M\Omega$ or $500M\Omega$ • μ F, whichever is less		
	Withstanding Voltage		nd discharge curi hstanding voltag	rent of the capaci ge measurement.	tor must not ex	ceed 50mA	Resist without problem		
Moisture	Appearance	A 6+		f F00 12 /	0 h		No problem observed		
Resistant Load	ΔC		•	ge for 500+12/ – Illow the parts to			Within±7.5% or ±0.75pF, whichever is larger		
	Q		nd discharge curi	ours, before meas rent of the capaci		ceed 50mA	C≥30pF: Q≥200 C<30pF: Q≥100+10C/3		
	IR	TOT IN THE asuf	ement.				Over $500M\Omega$ or $25M\Omega$ • μ F, whichever is less		
High-	Appearance	After applying	g *twice the rated	d voltage in the t	emperature of	125±3°C	No problem observed.		
Temperature Load	ΔC	for 1000+12/		ure the sample af			Within ±3% or ±0.3pF, whichever is larger		
Loud	Q	The charge ar for IR measur	nd dischargé curi ement.	rent of the capaci ve products are ir		ceed 50mA	C≥30pF : Q≥350 10pF <c<30pf 2<br="" :="" q≥275+5c="">C<10pF : Q≥200+10C</c<30pf>		
	IR	chart below.					Over $1000M\Omega$ or $50M\Omega$ • μ F, whichever is less		

Please ask for individual specification for the hatched range in previous chart.

Voltage to be applied in the High Temperature Load (Applied voltage is the multiple of the rated volatage)

Applied Voltage	Rated Voltage	Products
×1.0	16V	CM02C∆221
×1.2	25V	CM02CAR20-120





Test Conditions and Standards

Test Conditions and Specifications for High Dielectric Type (X5R, X7R, X7S) CM / CT Series (Standard Spec.1)

Test	Items	Test Conditions	Specifications
Capacitance Va	lue (C)	Measure after heat treatment	Within tolerance
Ταηδ		$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$	Refer to capacitance chart
Insulation Resis	tance (IR)	Apply the rated voltage for 1 minute, and measure it in normal temperature and humidity. The charge and discharge current of the capacitor must not exceed 50mA.	Over $10000M\Omega$ or $500M\Omega$ • μ F, whichever is less
Dielectric Resis	tance	Apply *2.5 times of the rated voltage for 1 to 5 seconds. *CM316X5R225, CM316X7S225/100V: twice The charge and discharge current of the capacitor must not exceed 50mA.	No problem observed
Appearance		Microscope	No problem observed
Termination Str	ength	Apply a sideward force of 500g (5N) to a PCB-mounted sample. note : 2N for 0201 size, and 1N for 01005 size. Exclude CT series with thickness of less than 0.66mm.	No problem observed
Bending Streng	th	Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds. Exclude CT series with thickness of less than 0.66mm.	No significant damage with 1mm bending
Vibration Test	Appearance	Take the initial value after heat treatment. Vibration frequency: 10 to 55 (Hz)	No problem observed
	ΔC	Amplitude: 1.5mm Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z directions: 2	Within tolerance
	Tanδ	hours each, 6 hours in total, and place in normal temperature and humidity, then measure the sample after heat treatment.	Within tolerance
Soldering Heat	Appearance	Take the initial value after heat treatment. Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in nor-	No problem observed
Resistant	ΔC	mal temperature and humidity, and measure after heat treatment.	Within±7.5%
	Tanδ	(Pre-heating conditions) Order Temperature Time	Within tolerance
	IR	1 80 to 100°C 2 minutes 2 150 to 200°C 2 minutes	Over $10000M\Omega$ or $500M\Omega$ • μ F, whichever is less
	Withstanding Voltage	The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Resist without problem
Solderablity		Soaking condition Sn-3Ag-0.5Cu 245±5°C 3±0.5 sec. Sn63 Solder 235±5°C 2±0.5 sec.	Solder coverage : 95% min.
Temperature	Appearance	Take the initial value after heat treatment.	No problem observed
Cycle	ΔC	(Cycle) Room temperature (3 min.)→	Within±7.5%
	Tanδ	Lowest operation temperature (30 min.)→ Room temperature (3 min.)→	Within tolerance
	IR	Highest operation temperature(30 min.)	Over $10000 \text{M}\Omega$ or $500 \text{M}\Omega$ • μF , whichever is less
	Withstanding Voltage	After 5 cycles, measure after heat treatment. The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Resist without problem
Moisture Resistant Load	Appearance	Take the initial value after heat treatment.	No problem observed
Resistant Load	ΔC	After applying rated voltage for 500+12/ –0 hours in the condition of 40°C±2°C and 90 to 95%RH, and place in normal temperature and humid-	Within±12.5%
	Tanδ	ity, then measure the sample after heat treatment. The charge and discharge current of the capacitor must not exceed 50mA	200% max. of initial value
	IR	for IR measurement.	Over $500 \mathrm{M}\Omega$ or $25 \mathrm{M}\Omega$ • μ F, whichever is less
High- Temperature	Appearance	Take the initial value after heat treatment. After applying *twice the rated voltage at the highest operation tempera-	No problem observed
Load	ΔC	ture for 1000+12/ –0 hours, and measure the sample after heat treatment in normal temperature and humidity.	Within±12.5%
	Tanδ	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	200% max. of initial value
	IR	*Apply 1.5 times when the rated voltage is 10V or less. Applied voltages for respective products are indicated in the chart below.	Over $1000 \text{M}\Omega$ or $50 \text{M}\Omega$ • μ F, whichever is less

Heat treatment Expose sample in the temperature of 150+0/ -10°C for 1 hour and leave the sample in normal temperature and humidity for 24±2 hours.

Voltage to be applied in the High Temperature Load (Applied voltage is the multiple of the rated voltage)

	1 3	1 (11 9 1 9)							
Applied Voltage	Rated Voltage	Products							
×1.0	10V	CM02X5R104							
^1.0	100V	CM316X5R225, CM316X7S225							
×1.3	×1.3 6.3V CM02X5R153-104, CT03X5R104								
	16V	CM02X5R101-103, CM05X5R224, CM105X5R225, CM21X5R106, CM316X5R226, CM02X7R101-222,							
		CM105X7R105, CM316X7R106, CM32X7R226, CT105X5R105, CT21X5R475							
×1.5	25V	CM03X5R332-103, CM105X5R105, CM21X5R225-475, CM316X5R106, CM32X5R106-226,							
	25V	CM05X7R104, CM21X7R105-225, CM316X7R475, CM32X7R106							
	50V	CM21X5R105, CM316X5R475, CM32X5R106, CM21X7R105, CM32X7R106, CT21X5R225,							

Please contact us for the optional specifications of the capacitance chart.





Test Conditions and Standards

Test Conditions and Specifications for High Dielectric Type (X5R, X6S, X7R, X7S, X7T) CM / CT Series (Standard Spec.2)

Test	Items	Test Conditions	Specifications
Capacitance Va	lue (C)	Measure after heat treatment	Within tolerance
Ταηδ		Capacitance Frequency Volt C≤10µF 1kHz±10% 1.0±0.2Vrms *1kHz±10% 0.5±0.2Vrms *2 10µF 120Hz±10% 0.5±0.2Vrms *CM02X5R474M06A#, CM03X5R225□06A#, 0.5±0.2Vrms *CM3X5R225M06A#035, CM03X5R475M06A#055, 0.5±0.2Vrms CM3X5R475M04A#, CM05X5R106M06A#, 0.5±0.2Vrms CT05X5R475M06A#033 1.0±0.2Vrms The charge and discharge current of the capacitor must not exceed 50mA.	Refer to capacitance chart
Insulation Resis	tance (IR)	Apply the rated voltage for 1minute, and measure it in normal temperature and humidity. The charge and discharge current of the capacitor must not exceed 50mA.	Over 50MΩ•μF
Dielectric Resist	tance	Apply *2.5 times of the rated voltage for 1 to 5 seconds. *CM21X7S105, CM316X7S475/100V: twice The charge and discharge current of the capacitor must not exceed 50mA.	No problem observed
Appearance		Microscope	No problem observed
Termination Str	ength	Apply a sideward force of 500g (5N) to a PCB-mounted sample. note: 2N for 0201 size, and 1N for 01005 size. Exclude CT series with thickness of less than 0.66mm.	No problem observed
Bending Streng	th	Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds. Exclude CT series with thickness of less than 0.66mm.	No significant damage with 1mm bending
Vibration Test	Appearance	Take the initial value after heat treatment. Vibration frequency: 10 to 55 (Hz)	No problem observed
iest	ΔC	Amplitude: 1.5mm	Within tolerance
	Tanδ	Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z directions: 2 hours each, 6 hours in total, and place in normal temperature and humidity, then measure the sample after heat treatment.	Within tolerance
Soldering Heat	Appearance	Take the initial value after heat treatment. Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in nor-	No problem observed
Resistant	ΔC	mal temperature and humidity, and measure after heat treatment. (Pre-heating conditions)	Within±7.5%
	Tanδ	Order Temperature Time	Within tolerance
	IR	1 80 to 100°C 2 minutes 2 150 to 200°C 2 minutes	Over 50MΩ•μF
	Withstanding Voltage	The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Resist without problem
Solderablity		Soaking condition Sn-3Ag-0.5Cu 245±5°C 3±0.5 sec. Sn63 Solder 235±5°C 2±0.5 sec.	Solder coverage : 95% min.
Temperature Cycle	Appearance	Take the initial value after heat treatment. (Cycle)	No problem observed
Cycle	ΔC	Room temperature (3 min.)→Lowest operation temperature (30	Within±7.5%
	Tanδ	min.)→Room temperature (3 min.)→Highest operation temperature(30 min.)	Within tolerance
	IR Withstanding Voltage	After 5 cycles, measure after heat treatment. The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Over $50M\Omega \cdot \mu F$ Resist without problem
Moisture	Appearance	Take the initial value after heat treatment.	No problem observed
Resistant Load	ΔC	After applying rated voltage for 500+12/ –0 hours in the condition of 40°C±2°C and 90 to 95%RH, and place in normal temperature and humid-	Within±12.5%
	Tanδ	ity, then measure the sample after heat treatment.	200% max. of initial value
	IR	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	Over 10MΩ•μF
High- Temperature	Appearance	Take the initial value after heat treatment. After applying * times the rated voltage at the highest operation tempera-	No problem observed
Load	ΔC	ture for 1000+12/ -0 hours, and measure the sample after heat treatment in normal temperature and humidity.	Within±12.5%
	Tanδ	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	200% max. of initial value
	IR	*Apply 1.0 times when the rated voltage is 4V or less. Applied voltages for respective products are indicated in the chart below.	Over 10MΩ•μF

Heat treatment Expose sample in the temperature of 150+0/ -10°C for 1 hour and leave the sample in normal temperature and humidity for 24±2 hours.

Voltage to be applied in the High Temperature Load (Applied voltage is the multiple of the rated voltage)

9		3 1 11 3 1
Applied Voltage	Rated Voltage	Products
	6.3V	CM02X5R224, CM02X5R474, CM03X5R225, CM03X5R475, CM05X5R106 CM05X5R156, CM05X5R226, CM21X5R476, CM03X6S105, CM105X6S226 CT05X5R105, CT05X5R225, CT05X5R475
	10V	CM03X5R225, CM105X5R226, CM21X6S226
×1.0	16V	CM03X5R105, CM05X5R225, CM05X5R475, CM105X5R226 CM21X6S226, CM21X7R475
	25V	CM05X5R105, CM05X5R225, CM05X5R475,CM105X5R475 CM105X5R106, CM21X5R226
	35V	CM05X5R105, CM105X5R475, CM105X5R106
	100V	CM21X7S105, CM316X7S475

Applied Voltage	Rated Voltage	Products					
×1.2	6.3V	CM03X5R105					
	6.3V	CM03X5R474					
×1.3	10V	CM03X5R223-224, CM05X5R105-225					
	16V	CM05X5R105					
	6.3V	CM21X6S226, CM05X7S105					
	0.5 V	CM105X7T106, CM21X7T226					
×15	10V	CM03X5R105, CM05X5R474, CM05X5R475,					
^ 1.5	100	CM21X5R226, CM105X6S106, CM105X7T475					
	25V	CM105X7R105, CM316X7R106					
	50V	CM316X7R475					






Test Conditions and Standards

Substrate for Adhesion Strength Test, Vibration Test, Soldering Heat Resistance Test, Temperature Cycle Test, Load Humidity Test, High-Temperature with Loading Test.


(Unit: mm)



Size (EIA Code)	a	b	С
02 (01005)	0.15	0.5	0.2
03 (0201)	0.26	0.92	0.32
05 (0402)	0.4	1.4	0.5
105 (0603)	1.0	3.0	1.2
21 (0805)	1.2	4.0	1.65
316 (1206)	2.2	5.0	2.0
32 (1210)	2.2	5.0	2.9


Substrate for Bending Test

(Unit: mm)



*02, 03, 05 size 0.8±0.1mm

Structure



About official Standards Certification

- The sites that manufacture the products listed in this catalog have acquired ISO 9001 quality management system (certification).
- The production site is Kagoshima Kokubu Plant.






(Unit: mm)

1.0

Packaging Options Tape and Reel

Reel



4.35±0.3

 9.5 ± 1.0

6.95±1.0


16.5 max.


 2.0 ± 0.5

E C	W ₂
R	B
→ A	_ W 1

Carrier Tape (Unit: mm)

F=1mm (02 Size)






F=2mm (02, 03, 05 Size)

7-inch Reel


(CODE: P) 13-inch Reel


(CODE: L, N, W)




F=4mm (105, 21, 316, 32 Size)

F=1mm (03, 05 Size)







(Unit: mm)

Size	Α	В	С	D	Е	F	G	Н		Carrie	r Tape
(EIA Code)	A	Ь	C	D	_		G	П	,	Width	Material
02 (01005)*	0.24±0.02	0.44±0.02	4.0±0.08	1.8±0.02	0.9±0.05	1.0±0.02	_	2.0±0.04	0.8±0.04	4mm	Plastic
02 (01003)	0.25±0.03	0.45±0.03	8.0±0.3	3.5±0.05	1.75±0.1	2.0±0.05		4.0±0.1	1.5+0.1/-0	8mm	Paper
	0.37±0.03	0.67±0.03	8.0+0.3/-0.1	3.5±0.05	1.75±0.1	1.0±0.05	_	4.0±0.05	1.5+0.1/-0		
	0.57 ± 0.05	0.07 ± 0.03	8.0 ± 0.3	3.3±0.03	1.75±0.1	2.0±0.05		4.0±0.1	1.5+0.1/-0		
03 (0201)*	0.39 ± 0.03	0.69±0.03	8.0±0.3	3.5±0.05	1.75±0.1	2.0±0.05	_	4.0±0.1	1.5+0.1/-0	8mm	Paper
	0.42±0.03	0.72±0.03	8.0±0.3	3.5±0.05	1.75±0.1	2.0±0.05	_	4.0±0.1	1.5+0.1/-0		
	0.44±0.05	0.74±0.05	8.0±0.3	3.5±0.05	1.75±0.1	2.0±0.05	_	4.0±0.1	1.5+0.1/-0		
	0.65±0.1		8.0+0.3/-0.1			1.0±0.05	_	4.0±0.05			
05 (0402)*	0.65±0.1	1.15±0.1	8.0±0.3	3.5±0.05	1.75±0.1	2.0±0.05	_	4.0±0.1	1.5+0.1/-0	8mm	Paper
03 (0402)	0.75±0.1		0.0±0.3			2.0±0.03		4.0±0.1		OIIIIII	Taper
	0.8±0.1	1.3±0.1	8.0 ± 0.3	3.5±0.05	1.75±0.1	2.0±0.05	_	4.0±0.1	1.5+0.1/-0		
105 (0603)*	1.0±0.2	1.8±0.2	8.0 ± 0.3	3.5 ± 0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	1.5+0.1/-0	8mm	Paper
103 (0003)	1.1±0.2	1.9±0.2	8.0 ± 0.3	3.5 ± 0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	1.5+0.1/-0	OIIIIII	
21 (0805)	1.5±0.2	2.3±0.2	8.0±0.3	3.5±0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	1.5+0.1/-0	8mm	Paper
21 (0003)	1.3±0.2	2.3 ± 0.2	0.0±0.3	3.3±0.03	1.73±0.1	4.0±0.1	2.0±0.03	4.0±0.1	1.3 10.1/ 0	8mm	Plastic
316 (1206)	2.0±0.2	3.6±0.2	8.0±0.3	3.5±0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	1.5+0.1/-0	8mm	Paper
, ,		3.0±0.2	0.0±0.3	3.3±0.03		4.0±0.1		4.0±0.1		8mm	Plastic
32 (1210)	2.9±0.2	3.6±0.2	8.0 ± 0.3	3.5±0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	1.5+0.1/-0	8mm	Plastic


^{*} Option






Packaging Options

Detail of leader and trailer



Adhesive tape

- 1) The exfoliative strength when peeling off the top tape from the carrier tape by the method of the following figure shall be *0.1 to 0.7N. *02 Size: 0.1 to 0.5N
- 2) When the top tape is peeled off, the adhesive stays on the top tape.
- 3) Chip capacitors will be in a state free without being stuck on the thermal adhesive tape.



Carrier tape

- 1) Chip will not fall off from carrier tape or carrier tape will not be damaged by bending than within a radius of 25mm.
- 2) The chip are inserted continuously without any empty pocket.
- 3) Chip will not be mis-mounted because of too big clearance between components and cavity. Also the waste of carrier tape will not fill a nozzle hole of mounting machine.






Surface Mounting Information

Dimensions for recommended typical land

Since the amount of solder (size of fillet) to be used has direct influence on the capacitor after mounting, the sufficient consideration is necessary.

When the amounts of solder is too much, the stress that a capacitor receives becomes larger. It may become the cause of a crack in the capacitor. When the land design of printed wiring board is considered, it is necessary to set up the form and size of land pattern so that the amount of solder is suitable.



General	(Unit: mm)


Size	Dime	nsion	Recomme	ended land di	mensions	
(EIA Code)	L	W	а	b	С	
02 (01005)	0.4±0.02	0.2±0.02	0.13 to 0.2	0.12 to 0.18	0.2 to 0.23	
	0.6±0.03	0.3±0.03	0.2 to 0.25	0.25 to 0.35	0.3 to 0.4	
03 (0201)	0.6±0.05	0.3±0.05	0.2 10 0.23	0.23 10 0.33	0.5 10 0.4	
	0.6±0.09	0.3±0.09	0.23 to 0.3	0.25 to 0.35	0.3 to 0.45	
	1.0±0.05	0.5±0.05	0.3 to 0.5	0.35 to 0.45	0.4 to 0.6	
05 (0402)	1.0±0.15	0.5±0.15	0.4 to 0.6	0.4 to 0.5	0.5 to 0.75	
	1.0±0.2	0.5±0.2	0.4 10 0.6	0.4 (0 0.5	0.5 (0 0.75	
	1.6±0.1	0.8±0.1	0.7 to 1.0	0.8 to 1.0	0.6 to 0.9	
105 (0603)	1.6±0.15	0.8±0.15				
103 (0003)	1.6±0.2	0.8 ± 0.2	0.8 to 1.0	0.8 to 1.0	0.8 to 1.1	
	1.6±0.25	0.8±0.25				
	2.0±0.1	1.25±0.1	1.0 to 1.3	1.0 to 1.2	1.0 to 1.45	
21 (0805)	2.0±0.15	1.25±0.15	1.0 to 1.3	1.0 to 1.2	1.25 to 1.55	
	2.0±0.2	1.25±0.2	1.0 to 1.3	1.0 to 1.2	1.23 (0 1.33	
	3.2±0.2	1.6±0.15	2.1 to 2.5	1.1 to 1.3	1.4 to 1.9	
316 (1206)	3.2±0.2	1.6±0.2	2.1 to 2.5	1.1 to 1.3	1.6 to 2.0	
	3.2±0.3	1.6±0.3	2.1 (0 2.5	1.1 (0 1.5	1.0 (0 2.0	
32 (1210)	3.2±0.3	2.5±0.2	2.1 to 2.5	1.1 to 1.3	1.9 to 2.8	

^{*} Recommended land dimensions may differ depending on dimensional tolerance.

Design of printed circuit and Soldering

The recommended fillet height shall be 1/2 of the thickness of capacitors or 0.5mm. When mounting two or more capacitors in the common land, it is necessary to separate the land with the solder resist strike so that it may become the exclusive land of each capacitor.

Ideal Solder Height



Item	Prohibited	Recommended example : Separation by solder resist
Multiple parts mount		Solder resist
Mount with leaded parts	Leaded parts	Solder resist Leaded parts
Wire soldering after mounting	Soldering iron Wire	Solder resist
Side by side layout	Solder resist	Solder resist






Surface Mounting Information

Mounting Design


The chip could crack if the PCB warps during processing after the chip has been soldered.

Recommended chip position on PCB to minimize stress from PCB warpage



Actual Mounting

- 1) If the position of the vacuum nozzle is too low, a large force may be applied to the chip capacitor during mounting, resulting in cracking.
- 2) During mounting, set the nozzle pressure to a static load of 1 to 3 N.
- 3) To minimize the shock of the vaccum nozzle, provide a support pin on the back of the PCB to minimize PCB flexture.



4) Bottom position of pick up nozzle should be adjusted to the top surface of a substrate which camber is corrected.

Resin Mold

- 1) If a large amount of resin is used for molding the chip, cracks may occur due to contraction stress during curing. To avoid such cracks, use a low shrinkage resin.
- 2) The insulation resistance of the chip will degrade due to moisture absorption. Use a low moisture absorption resin.
- 3) Check carefully that the resin does not generate a decomposition gas or reaction gas during the curing process or during normal storage. Such gases may crack the chip capacitor or damage the device itself.






Surface Mounting Information


Soldering Method


- 1) Ceramic is easily damaged by rapid heating or cooling. If some heat shock is unavoidable, preheat enough to limit the temperature difference (Delta T) to within 150 degree Celsius.
- 2) The product size 1.6×0.8mm to 3.2×1.6mm can be used in reflow and wave soldering, and the product size of bigger than 3.2×1.6mm, or smaller than 1.6×0.8mm can be used in reflow.
 - Circuit shortage and smoking can be created by using capacitors which are used neglecting the above caution.
- 3) Please see our recommended soldering conditions.
- 4) In case of using Sn-Zn Solder, please contact us in advance.
- 5) The following condition is recommended for spot heater application.

Recommended spot heater condition

Item	Condition
Distance	5mm min.
Angle	45°
Projection Temp.	400°C max.
Flow rate	Set at the minimum
Nozzle diameter	2φ to 4φ (Single hole type)
Application time	10 sec. max. (1206 and smaller) 30 sec. max. (1210 and larger)











Precautions

Circuit Design

- 1. Once application and assembly environments have been checked, the capacitor may be used in conformance with the rating and performance which are provided in both the catalog and the specifications. Use exceeding that which is specified may result in inferior performance or cause a short, open, smoking, or flaming to occur, etc.
- 2. Please consult the manufacturer in advance when the capacitor is used in devices such as: devices which deal with human life, i.e. medical devices; devices which are highly public orientated; and devices which demand a high standard of liability.
 Accident or malfunction of devices such as medical devices, space equipment and devices having to do with atomic power could generate grave consequence with respect to human lives or, possibly, a portion of the
- public. Capacitors used in these devices may require high reliability design different from that of general purpose capacitors.3. Please use the capacitors in conformance with the operating temperature provided in both the catalog and the
- specifications.

 Be especially cautious not to exceed the maximum temperature. In the situation the maximum temperature set forth
 - in both the catalog and specifications is exceeded, the capacitor's insulation resistance may deteriorate, power may suddenly surge and short-circuit may occur.
 - The capacitor has a loss, and may self-heat due to equivalent series resistance when alternating electric current is passed therethrough. As this effect becomes especially pronounced in high frequency circuits, please exercise caution.
 - When using the capacitor in a (self-heating) circuit, please make sure the surface of the capacitor remains under the maximum temperature for usage. Also, please make certain temperature rises remain below 20°C.
- 4. Please keep voltage under the rated voltage which is applied to the capacitor. Also, please make certain the peak voltage remains below the rated voltage when AC voltage is super-imposed to the DC voltage. In the situation where AC or pulse voltage is employed, ensure average peak voltage does not exceed the rated voltage. Exceeding the rated voltage provided in both catalog and specifications may lead to defective withstanding voltage or, in worst case situations, may cause the capacitor to smoke or flame.
- 5. When the capacitor is to be employed in a circuit in which there is continuous application of a high frequency voltage or a steep pulse voltage, even though it is within the rated voltage, please inquire to the manufacturer. In the situation the capacitor is to be employed using a high frequency AC voltage or a extremely fast rising pulse voltage, even though it is within the rated voltage, it is possible capacitor reliability will deteriorate.
- 6. It is a common phenomenon of high-dielectric products to have a deteriorated amount of static electricity due to the application of DC voltage.

 Due caution is necessary as the degree of deterioration varies depending on the quality of capacitor materials, capacity, as well as the load voltage at the time of operation.
- 7. Do not use the capacitor in an environment where it might easily exceed the respective provisions concerning shock and vibration specified in the catalog and specifications.


 In addition, it is a common piezo phenomenon of high dielectric products to have some voltage due to vibration or to have noise due to voltage change. Please contact sales in such case.
- 8. If the electrostatic capacity value of the delivered capacitor is within the specified tolerance, please consider this when designing the respective product in order that the assembled product function appropriately.
- 9. Please contact us upon using conductive adhesives.

Storage

Please note the following regarding the storage of delivered products.

- 1. Set the storage temperature to + 5 to + 40 $^{\circ}$ C and humidity to 20 \sim 70% RH. Other meteorological conditions are in accordance with classification 1 K2 of JIS C 60721 -3 -1.
- 2. Store in a place where corrosive gas (H₂S, SO₂, NO₂, Cl₂, etc.) does not exist in the atmosphere. Also, avoid exposure to salty moisture. In either case, this may cause oxidation corrosion of the terminal electrode, reducing solderability.
- If you store the above delivered products according to the conditions listed above, it will satisfy the solderability standard for 6 months from the shipping date.

Safety application guideline and detailed information of electrical properties are also provided in kyocera web site; URL: https://ele.kyocera.com/en/product/capacitor/






General CM02 Series Size (JIS Code): 01005(0402) # Packaging Code (Packaging quantity): H(20,000pcs.) / N(80,000pcs.) / P(40,000pcs.)

Dielectric code	Canacitance	□:Tolerance	Voltage	Part Number	Q		Dimension			
СФ	Capacitance	□.Toterarice	[V]	Tart Number	ų	L[mm]	W[mm]	T[mm]	Code (quantity)	
	1pF			CM02CΔ1R0□25A#	420	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	1.5pF			CM02CΔ1R5□25A#	430	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	2pF	P++0.1pE / C++0.2EpE	25	CM02CΔ2R0□25A#	440	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	3pF	B:±0.1pF / C:±0.25pF	25	CM02CΔ3R0□25A#	460	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	4pF			CM02CΔ4R0□25A#	480	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	5pF			CM02CΔ5R0□25A#	500	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	6pF			CM02CΔ6R0□25A#	520	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	7pF	C++0.25=5 / D++0.5=5	25	CM02CΔ7R0□25A#	540	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	8pF	C:±0.25pF / D:±0.5pF		CM02CΔ8R0□25A#	560	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	9pF			CM02CΔ9R0□25A#	580	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	10pF	J:±5% / K:±10%	25	CM02CΔ100□25A#	600	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
CG/CH	12pF			CM02CΔ120□25A#	640	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
CG/CH	15pF			CM02CΔ150□25A#	700	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	18pF			CM02CΔ180□25A#	760	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	22pF			CM02CΔ220□25A#	840	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	27pF			CM02CΔ270□16A#	940	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	33pF			CM02CΔ330□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	39pF			CM02CΔ390□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	47pF			CM02CΔ470□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	56pF	J:±5% / K:±10%	16	CM02CΔ560□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	68pF			CM02CΔ680□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	82pF			CM02CΔ820□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	100pF			CM02CΔ101□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	220pF			CM02CΔ221□16A#	1000	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	

General CM03 Series Size (JIS Code): 0201(0603) # Packaging Code (Packaging quantity): H(15,000pcs.) / N(50,000pcs.) / Q(30,000pcs.) / W(150,000pcs.)

Dielectric code	Canacitance	Capacitance	Voltage	Part Number	Q		# Packaging Code		
СФ	capacitance	Capacitance	[V]	Tart Number		L[mm]	W[mm]	T[mm]	(quantity)
	1pF			CM03CΔ1R0□50A#	420	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	1.5pF			CM03CΔ1R5□50A#	430	0.6 ± 0.03	0.3±0.03	0.3 ± 0.03	H/N/Q/W
	2pF	B:±0.1pF / C:±0.25pF	50	CM03CΔ2R0□50A#	440	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	3pF	B.±0.1pr / C.±0.25pr	30	CM03CΔ3R0□50A#	460	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	4pF			CM03CΔ4R0□50A#	480	0.6±0.03	0.3±0.03	0.3 ± 0.03	H/N/Q/W
	5pF			CM03CΔ5R0□50A#	500	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	6pF	C:±0.25pF / D:±0.5pF		CM03CΔ6R0□50A#	520	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	7pF		50	CM03CΔ7R0□50A#	540	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	8pF			CM03CΔ8R0□50A#	560	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	9pF			CM03CΔ9R0□50A#	580	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	10pF			CM03CΔ100□50A#	600	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
CG/CH	12pF			CM03CΔ120□50A#	640	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	15pF			CM03CΔ150□50A#	700	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	18pF			CM03CΔ180□50A#	760	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	22pF			CM03CΔ220□50A#	840	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	27pF			CM03CΔ270□50A#	940	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	33pF	J:±5% / K:±10%	50	CM03CΔ330□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	39pF			CM03CΔ390□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	47pF			CM03CΔ470□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	56pF			CM03CΔ560□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	68pF			CM03CΔ680□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	82pF			CM03CΔ820□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	100pF			CM03CΔ101□50A#	1000	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W






General CM02 Series Size (JIS Code): 01005(0402) # Packaging Code (Packaging quantity): H(20,000pcs.) / N(80,000pcs.) / P(40,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		# Packaging Code			
Dielectric code	Capacitance	ii. Tolerance	[V]	Fait Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)	
	100pF			CM02X5R101 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	150pF			CM02X5R151 ₁ 16A#	12.5	0.4 ± 0.02	0.2±0.02	0.2±0.02	H/N/P	
	220pF			CM02X5R221 = 16A#	12.5	0.4 ± 0.02	0.2±0.02	0.2±0.02	H/N/P	
	330pF			CM02X5R331 ₁ 16A#	12.5	0.4 ± 0.02	0.2±0.02	0.2±0.02	H/N/P	
	470pF			CM02X5R471 ₁ 16A#	12.5	0.4 ± 0.02	0.2±0.02	0.2±0.02	H/N/P	
	680pF			CM02X5R681 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	1000pF	K:±10% / M:±20%	16	CM02X5R102 _{16A} #	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	1500pF			CM02X5R152 = 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	2200pF			CM02X5R222 = 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	3300pF			CM02X5R332 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
X5R	4700pF			CM02X5R472 = 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
ASK	6800pF			CM02X5R682 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	10000pF			CM02X5R103 = 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	15000pF	K:±10% / M:±20%		CM02X5R153 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	22000pF			CM02X5R223 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	33000pF		K:±10% / M:±20%	6.3	CM02X5R333 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P
	47000pF				CM02X5R473 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P
	68000pF				CM02X5R683 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P
	0.15		10	CM02X5R104□10A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	0.1µF	μ ^F K:±10% / M:±20%		CM02X5R104 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	0.22µF		6.3	CM02X5R224 = 06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	0.47µF	M:±20%	1	CM02X5R474M06A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	100pF			CM02X7R101 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	150pF			CM02X7R151 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	220pF			CM02X7R221 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	330pF			CM02X7R331 ₂ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
X7R	470pF	K:±10% / M:±20%	16	CM02X7R471 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	680pF			CM02X7R681 ₁ 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	1000µF			CM02X7R102□16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	1500µF			CM02X7R152□16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	
	2200µF			CM02X7R222 16A#	12.5	0.4±0.02	0.2±0.02	0.2±0.02	H/N/P	

General CM03 Series Size (JIS Code): 0201(0603) # Packaging Code (Packaging quantity): H(15,000pcs.) (*10,000pcs.) / N(50,000pcs.) / Q(30,000pcs.) / W(150,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		# Packaging Code		
Dielectric code	Capacitance	ii.Tolerance	[V]	Part Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)
	3300pF			CM03X5R332 = 25A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	4700pF		25	CM03X5R472 = 25A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	6800pF		25	CM03X5R682 = 25A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	10000pF			CM03X5R103 = 25A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	22000pF			CM03X5R223 = 10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	33000pF			CM03X5R333 = 10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	47000pF	K:±10% / M:±20%	10	CM03X5R473 = 10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	68000pF			CM03X5R683 = 10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	0.1µF			CM03X5R104□10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
I			25	CM03X5R224□25A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
X5R	0.22µF		16	CM03X5R224 = 16A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
ASK			10	CM03X5R224 = 10A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	0.47µF		6.3	CM03X5R474 = 06A#	12.5	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	1μF	M:±20%	16	CM03X5R105M16A#	20.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
			10	CM03X5R105M10A#	20.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
				CM03X5R105M10A#035	12.5	0.6±0.05	0.3±0.05	0.3±0.05	H/N/Q/W
		K:±10% / M:±20%	6.3	CM03X5R105 = 06A#	12.5	0.6±0.05	0.3±0.05	0.3±0.05	H/N/Q/W
		M:±20%	10	CM03X5R225M10A#	15.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
	2.2µF	2.2µF K:±10% / M:±20%	6.3	CM03X5R225 = 06A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
	· .			CM03X5R225M06A#035	12.5	0.6±0.05	0.3±0.05	0.3±0.05	H/N/Q/W
	4.7µF	M:±20%		CM03X5R475M06AH055	15.0	0.6±0.09	0.3±0.09	0.5±0.05	H(*)
	4.7µF		4	CM03X5R475M04A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
			10	CM03X6S105M10A#	20.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
X6S	1μF	M:±20%	6.3	CM03X6S105M06A#039	20.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
X02		IVI:±20%	4	CM03X6S105M04A#039	20.0	0.6±0.09	0.3±0.09	0.3±0.09	H/N
	4.7µF		2.5	CM03X6S475M02AH055	15.0	0.6±0.09	0.3±0.09	0.5±0.05	H(*)
	0.22µF	K:±10% / M:±20%	10	CM03X6T224 = 10A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
х6Т	1μF		2.5	CM03X6T105M02A#035	12.5	0.6±0.05	0.3±0.05	0.3±0.05	H/N/Q/W
X61	22.5	M:±20%	4	CM03X6T225M04A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
	2.2µF		2.5	CM03X6T225M02A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N
	3300pF			CM03X7R332□10A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
V7D	4700pF	K 100/ / M 200/	10	CM03X7R472 = 10A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
X7R	6800pF	K:±10% / M:±20%	10	CM03X7R682□10A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
	10000pF			CM03X7R103□10A#	5.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
X7S	0.1µF	K:±10% / M:±20%	6.3	CM03X7S104□06A#	10.0	0.6±0.03	0.3±0.03	0.3±0.03	H/N/Q/W
X7T	1µF	M:±20%	6.3	CM03X7T105M06A#	12.5	0.6±0.09	0.3±0.09	0.3±0.09	H/N






 $General\ CM05\ Series\ Size\ (JIS\ Code)\ \ :\ 0402(1005)\ \#\ Packaging\ Code\ (Packaging\ quantity)\ \ :\ H(10,000pcs.)\ /\ N(50,000pcs.)(*40,000pcs.)(**30,000pcs.)\ /\ Q(20,000pcs.)\ /\ W(100,000pcs.)$

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		Dimension	# Packaging Code	
Dielectric code	Capacitance	□.Toterance	[V]	Part Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)
	0.1µF		25	CM05X5R104 = 25A#	5.0	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	0.22µF		16	CM05X5R224a16A#	12.5	1.0±0.05			H/N/Q/W
	0.47µF		10	CM05X5R474 = 10A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
		K:±10% / M:±20%	35	CM05X5R105 = 35A#	10.0	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	1µF		25	CM05X5R105 = 25A#	10.0	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	iμr		16	CM05X5R105□16A#	10.0	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
			10	CM05X5R105 = 10A#	10.0	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
		M:±20%	35	CM05X5R225M35A#	12.5	1.0±0.2		0.5±0.2	H / N(*)
		IVI:±20%	25	CM05X5R225M25A#	12.5	1.0±0.2	5 0.5±0.05 0.5±0.05 5 0.5±0.15 0.5±0.15 6 0.5±0.2 0.5±0.2 6 0.5±0.2 0.5±0.2 7 0.5±0.2 0.5±0.2 7 0.5±0.2 0.5±0.2 8 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.2 9 0.5±0.2 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05 9 0.5±0.05 0.5±0.05	H / N(*)	
	2.2µF			CM05X5R225 = 25A#055	12.5	1.0±0.2		0.55 max.	H/N
		K:±10% / M:±20%	16	CM05X5R225 = 16A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
X5R			10	CM05X5R225 = 10A#	12.5	1.0±0.05			H/N/Q/W
			25	CM05X5R475M25A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
	4.7µF		16	CM05X5R475M16A#	12.5	1.0±0.2	M M mm T mm 10.05	H / N(*)	
	4.7μΓ			CM05X5R475M10A#	12.5	1.0±0.2		0.5±0.2	H / N(*)
			10	CM05X5R475M10A#065	12.5	1.0±0.15	0.5±0.15		H / N(*)
	10 5			CM05X5R106M10A#	12.5	1.0±0.2	0.5±0.2	5 0.5±0.15 2 0.5±0.2 2 0.5±0.2	H / N(*)
	10μF	M:±20%	6.3	CM05X5R106M06A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
	15µF		6.3				H / N(*)		
	15µF		4	CM05X5R156M04A#	12.5	1.0±0.15	0.5±0.15	0.5±0.15	H / N(*)
			6.3	CM05X5R226M06A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
	22µF		6.3	CM05X5R226M06A#080	12.5	1.0±0.2	0.5±0.2	0.8 max.	H / N(**)
			4	CM05X5R226M04A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
	0.47.5		16	CM05X6S474M16A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	0.47µF			CM05X6S474M10A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	1µF		10	CM05X6S105M10A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
X6S	,	M:±20%		CM05X6S475M10A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
702	4.7µF	IVI:±20%		CM05X6S475M06A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
			6.3	CM05X6S475M06A#065	12.5	1.0±0.15	0.5±0.15	0.5±0.15	H / N(*)
	10µF			CM05X6S106M06A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)
	22µF		4	CM05X6S226M04A#080	12.5	1.0±0.2	0.5±0.2	0.8 max.	H / N(**)
VZD	0.1µF	K-+100/ / M-+200/	25	CM05X7R104 25A#	12.5	1.0±0.05			H/N/Q/W
X7R	0.47µF	K:±10% / M:±20%	6.3	CM05X7R474 = 06A#	12.5	1.0±0.05	0.5±0.05	0.5±0.05	H/N/Q/W
	1uF	K:±10% / M:±20%	6.3	CM05X7S105 = 06A#	12.5	1.0±0.05	0.5±0.05		H/N/Q/W
	IμF	M:±20%	4	CM05X7S105M04A#	12.5	1.0±0.05			H/N/Q/W
X7S		K:±10% / M:±20%	10	CM05X7S225 10A#065	5.0	1.0±0.15	0.5±0.15	0.5±0.15	H / N(*)
	2.2µF		6.3	CM05X7S225 06A#065	5.0	1.0±0.15	0.5±0.15	0.5±0.15	H / N(*)
		M:±20%	4	CM05X7S225M04A#065	5.0	1.0±0.15	0.5±0.15	0.5±0.15	H / N(*)
X7T	4.7µF	M:±20%	10	CM05X7T475M10A#	12.5	1.0±0.2	0.5±0.2	0.5±0.2	H / N(*)

General CM105 Series Size (JIS Code): 0603(1608) # Packaging Code (Packaging quantity): T(4,000pcs.) / L(10,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		Dimension	# Packaging Code	
Dielectric code	Capacitance	1. Tolerance	[V]	rait Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)
	1µF		25	CM105X5R105 = 25A#	12.5	1.6±0.15	0.8±0.15	0.8±0.15	T/L
	2.2µF		16	CM105X5R225 = 16A#	12.5	1.6±0.1	0.8±0.1	0.8±0.1	T/L
		K:±10% / M:±20%	35	CM105X5R475 = 35A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	4.7µF		25	CM105X5R475 = 25A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
VED	,		10	CM105X5R475 = 10A#	12.5	1.6±0.15	0.8±0.15	0.8±0.15	T/L
X5R	10	M:±20%	35	CM105X5R106M35A#	15.0	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	10μF	K:±10% / M:±20%	25	CM105X5R106 = 25A#	15.0	1.6±0.2	0.8±0.2 0.8±0.2 0.8±0.2 0.8±0.2 0.8±0.2	0.8±0.2	T/L
	22.5		16	CM105X5R226M16A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	22µF	M:±20%	10	CM105X5R226M10A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	47µF		6.3	CM105X5R476M06A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	10	M:±20%	16	CM105X6S106M16A#	15.0	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	10μF	K:±10% / M:±20%	10	CM105X6S106□10A#	15.0	1.6±0.2	0.8±0.2	0.8±0.2	T/L
X6S			10	CM105X6S226M10A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	22µF	M:±20%	6.3	CM105X6S226M06A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
		M:±20%	4	CM105X6S226M04A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	47µF		F	4	CM105X6S476M04A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2
			25	CM105X7R105 = 25A#	5.0	1.6±0.1	0.8±0.1	0.8±0.1	T/L
X7R	1µF	K:±10% / M:±20%	16	CM105X7R105 = 16A#	12.5	1.6±0.1	0.8±0.1	0.8±0.1	T/L
\ ^/K	·	N.±10% / IVI:±20%	10	CM105X7R105 = 10A#	12.5	1.6±0.1	0.8±0.1	0.8±0.1	T/L
	2.2µF		6.3	CM105X7R225 = 06A#	12.5	1.6±0.15	0.8±0.15	0.8±0.15	T/L
	4.7µF	K:±10% / M:±20%	10	CM105X7T475 = 10A#	12.5	1.6±0.2	0.8±0.2	0.8±0.2	T/L
X7T	10	M:±20%	10	CM105X7T106M10A#	15.0	1.6±0.2	0.8±0.2	0.8±0.2	T/L
	10μF		6.3	CM105X7T106M06A#	15.0	1.6±0.2	0.8±0.2	0.8±0.2	T/L





General CM21 Series Size (JIS Code): 0805(2012) # Packaging Code (Packaging quantity): T(3,000pcs.) / L(10,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		Dimension		# Packaging Code
Dielectric code	Capacitance	□.Tolerance	[V]	Part Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)
	1μF		50	CM21X5R105 = 50A#	12.5	2.0±0.1	1.25±0.1	1.25±0.1	T/L
	2.2µF	K:±10% / M:±20%	25	CM21X5R225 = 25A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
	4.7µF	K.± 10/6 / WI.±20/6	23	CM21X5R475 = 25A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
X5R	10μF		16	CM21X5R106=16A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
XSIC	22µF		25	CM21X5R226M25A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
	22μΓ	M:±20%	10	CM21X5R226M10A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
	47µF	IVI.±2076	6.3	CM21X5R476M06A#	10.0	2.0±0.2	1.25±0.2	1.25±0.2	T/L
	100µF		4	CM21X5R107M04A#	12.5	2.0±0.2	1.25±0.2		T/L
			16	CM21X6S226M16A#	12.5	2.0±0.2	1.25±0.2		T/L
	22µF		10	CM21X6S226M10A#	12.5	2.0±0.2	1.25±0.2		T/L
X6S		M:±20%	6.3	CM21X6S226M06A#	12.5	2.0±0.2	1.25±0.2		T/L
	47µF		4	CM21X6S476M04A#	10.0	2.0±0.2	1.25±0.2		T/L
	100µF			CM21X6S107M04A#	12.5	2.0±0.2	1.25±0.2	1.1 1.25±0.1 1.25±0.2	T/L
	1uF		50	CM21X7R105 = 50A#	5.0	2.0±0.2	1.25±0.2		T/L
			25 CM21X7R105\(\tilde{2}\)5A# 12.5 2.0\(\tilde{2}\)6.1		1.25±0.1		T/L		
X7R	2.2µF	K:±10% / M:±20%		CM21X7R225 = 25A#	12.5	2.0±0.2	1.25±0.2		T/L
	4.7µF		16	CM21X7R475 = 16A#	12.5	2.0±0.2	1.25±0.2		T/L
	10µF		6.3	CM21X7R106□06A#	12.5	2.0±0.2	1.25±0.2		T/L
X7S	1μF	K:±10% / M:±20%	100	CM21X7S105 = 100A#	5.0	2.0±0.2	1.25±0.2	1.25±0.2	T/L
X7T	22µF	M:+20%	10	CM21X7T226M10A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L
^/1	22μΓ	22μF M:±20%	6.3	CM21X7T226M06A#	12.5	2.0±0.2	1.25±0.2	1.25±0.2	T/L

General CM316 Series Size (JIS Code): 1206(3216) # Packaging Code (Packaging quantity): T(2,500pcs.)(*2,000pcs.) / L(5,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage	Part Number	Tanδ		Dimension		# Packaging Code
	Capacitance	itolerance	[V] _	Part Number	[%]	L[mm]	W[mm]	T[mm]	(quantity)
	2.2µF		100	CM316X5R225 = 100A#	5.0	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	2.2μΓ		25	CM316X5R225 = 25A#	5.0	3.2±0.2	1.6±0.15	1.6±0.15	T/L
X5R	4.7µF	K:±10% / M:±20%	50	CM316X5R475 = 50A#	5.0	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	10μF		25	CM316X5R106 = 25A#	12.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	22µF		16	CM316X5R226 = 16A#	12.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	4.7µF		50	CM316X7R475 = 50A#	5.0	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	10.5		25	CM316X7R106 = 25A#	5.0	3.2±0.2	1.6±0.2	1.6±0.2	T/L
X7R	10μF	K:±10% / M:±20%	16	CM316X7R106 = 16A#	12.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	22µF		10	CM316X7R226 = 10A#	7.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L
			6.3	CM316X7R226 = 06A#	12.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L
X7S	2.2µF		100	CM316X7S225 = 100A#	5.0	3.2±0.2	1.6±0.2	1.6±0.2	T/L
	4.7µF	K:±10% / M:±20%	4.7µF K:±10% / M:±20%	100	CM316X7S475 = 100AT	5.0	3.2±0.3	1.6±0.3	1.6±0.3
	22µF		10	CM316X7S226 = 10A#	7.5	3.2±0.2	1.6±0.2	1.6±0.2	T/L

General CM32 Series Size (JIS Code): 1210(3225) # Packaging Code (Packaging quantity): T(1,000pcs.) / L(4,000pcs.)

Dielectric code	Capacitance	□:Tolerance	Voltage [V]	Part Number	Tanδ [%]		# Packaging Code		
						L[mm]	W[mm]	T[mm]	(quantity)
			50	CM32X5R106 = 50A#	5.0	3.2±0.3	2.5±0.2	2.5±0.2	T/L
X5R	10μF	K:±10% / M:±20%	25	CM32X5R106 = 25A#	12.5	3.2±0.3 3.2±0.3	2.5±0.2	2.5±0.2	T/L
		K.±10% / WI.±20%	16	CM32X5R106□16A#	5.0		2.5±0.2	2.5±0.2	T/L
	22µF		25	CM32X5R226 = 25A#	12.5	3.2±0.3	2.5±0.2	2.5±0.2	T/L
	10uF		50	CM32X7R106 = 50A#	5.0 3.2±0.3 2.5	2.5±0.2	2.5±0.2	T/L	
X7R	ΤΟμΓ	K:±10% / M:±20%	25	CM32X7R106=25A#	12.5	3.2±0.3	2.5±0.2	2.5±0.2	T/L
	22µF		16	CM32X7R226 = 16A#	12.5	3.2±0.3	2.5±0.2	2.5±0.2	T/L



Notes for Using the Catalog



- 1. Specifications described in this catalog are for references. Products specifications shall be based on written documents agreed by each party.
- 2. Contents in this catalog are subject to change without notice. It is recommended to confirm the latest information at the time of usage. Also, Kyocera Electronic Components Catalog is revised once a year. We may not be able to accept requests based on old catalogs.
- 3. Products in this catalog are intended to be used in general electronic equipment such as office equipment, audio and visual equipment, communication equipment, measurement instrument and home appliances. It is absolutely recommended to consult with our sales representatives in advance upon planning to use our products in applications which require extremely high quality and reliability such as aircraft and aerospace equipment, traffic systems, safety systems, power plant and medical equipment including life maintenance systems.
- 4. Even though we strive for improvements of quality and reliability of products, it is requested to design with enough safety margin in equipment or systems in order not to threaten human lives directly or damage human bodies or properties by an accidental result of products.
- 5. It is requested to design based on guaranteed specifications for such as maximum ratings, operating voltage and operating temperature. It is not the scope of our guarantee for unsatisfactory results due to misuse or inadequate usage of products in the catalog.
- 6. Operation summaries and circuit examples in this catalog are intended to explain typical operation and usage of the product. It is recommended to perform circuit and assembly design considering surrounding conditions upon using products in this catalog.
- 7. Technical information described in this catalog is meant to explain typical operations and applications of products, and it is not intended to guarantee or license intellectual properties or other industrial rights of the third party or Kyocera.
- 8. Trademarks, logos and brand names used in this catalog are owned by Kyocera or the corresponding third party.
- 9. Certain products in this catalog are subject to the Foreign Exchange and Foreign Trade Control Act of Japan, and require the license from Japanese Government upon exporting the restricted products and technical information under the law. Besides, it is requested not to use products and technical information in the catalog for the development and/or manufacture of weapons of mass destruction or other conventional weapons, nor to provide them to any third party with the possibility of having such purposes.
- 10. It is prohibited to reprint and reproduce a part or whole of this catalog without permission.
- 11. Contents described herein are as of February 2022.